



Aalborg Universitet

AALBORG UNIVERSITY
DENMARK

Several Key Factors Influencing Fracture and Tensile Strength of Glass fibers

An invited talk

Yue, Yuanzheng; Lund, Majbritt

Publication date:
2011

Document Version
Publisher's PDF, also known as Version of record

[Link to publication from Aalborg University](#)

Citation for published version (APA):

Yue, Y., & Lund, M. (2011). *Several Key Factors Influencing Fracture and Tensile Strength of Glass fibers: An invited talk*. Abstract from 5th International Workshop on Flow and Fracture of Advanced Glasses, St-Malo, France.

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal -

Take down policy

If you believe that this document breaches copyright please contact us at vbn@aub.aau.dk providing details, and we will remove access to the work immediately and investigate your claim.

Several Key Factors Influencing Fracture and Tensile Strength of Glass fibers

Yuanzheng Yue and Majbritt D. Lund

Section of Chemistry, Aalborg University, DK-9000 Aalborg, Denmark

Understanding of the fracture mechanism and tensile strength of glass and glass fibers has been a challenging subject for glass scientists over the past century. In the present work, we report our recent findings about the fracture behavior and the tensile strength of the oxide glass fibers. We found several key factors that considerably influence the tensile strength of both continuous glass fibers and discontinuous wool fibers. Based on a large amount of the tensile strength data, it is revealed that the fiber drawing force enhances the tensile strength of the oxide glass fibers. This enhancement could be attributed to the two factors: the structural anisotropy and the macroscopic defect (flaws, bubbles, striae et al) orientation, both of which are induced by the fiber drawing forces. This finding is further verified by annealing experiments on both continuous and wool fibers below T_g . The onset annealing temperature of the tensile strength decay is close to that of the anisotropy relaxation of the continuous fibers. The relative contributions of the different factors to the tensile strength are distinguished and estimated in terms of the tensile strength decay as a function of the sub- T_g annealing temperature in order to better understand the fracture mechanism of glass fibers. Furthermore, we illustrate both special and general fracture patterns of glass fibers. Finally, we demonstrate and explain how the tensile strength of the discontinuous wool fibers is related to the redox state of iron.